

## Test report

Request No. : KATRM210623-006 Request date : 2021. 06. 23  
Report No. : KAAAM210709-011 Issue date : 2021. 07. 09  
Company : SEIWA INDUSTRY Purpose of use : Quality control  
Address : 2-4-29, TATSUMI-NISHI, IKUNO, OSAKA, JAPAN  
Person : HWANG JUNG HWAN  
Submit company :  
Name of sample : SSM(EAR PLUGS FOAM TYPE)

Test item	Test result	
	Control	Sample
KS K 0693: 2016		
<i>Staphylococcus aureus</i> ATCC 6538	1.9 X 10 <sup>6</sup>	1.5 X 10 <sup>5</sup>
Inoculated bacteria	3.3 X 10 <sup>5</sup> CFU/mL	92.0


- ※ Sample: type – URETHANE
- ※ Control: Standard cotton
- ※ Sample treatment: 0.4 g of sample is used for test
- ※ Bacterial reduction rate(%)= [(average CFU of control after 24 hrs)-(average CFU of sample after 24 hrs)/ (average CFU of control after 24 hrs) X 100 (%)

Korea Analysis Test Researcher




- Result picture -

ATCC 6538



< Control >



< Sample >

Remark 1. This report is the result of test conducted by company's samples only. It does not guarantee the quality of all products.  
2. This report cannot be used for advertisement, campaign, and legal purpose without KATR's permission. Do not use for any other purposes.

- Sample picture -



< SSM(EAR PLUGS FOAM TYPE) >



Remark 1. This report is the result of test conducted by company's samples only. It does not guarantee the quality of all products.  
2. This report cannot be used for advertisement, campaign, and legal purpose without KATR's permission. Do not use for any other purposes.